



MIG WELD

20 rue Colbert / F-21600 LONGVIC / France **Téléphone**
/ Phone + 33 3 80 68 07 57 www.mig-weld.fr

CHINA CONTACT
86-21-68000970 18964889500
www.mig-weld.cn
info@mig-weld.cn

MIG WELD



The quality aluminium welding wire



www.mig-weld.fr



Chemical compositions / Compositions chimiques

Indicated values are maximum values (%) / Les valeurs indiquées sont les valeurs maximales (%)											Unspecified elements / Éléments non spécifiés		
	Si	Fe	Cu	Mn	Mg	Cr	Zn	Be	Ti	Zr	Single / Séparément	Total	Al
ML 1070	0,20	0,25	0,04	0,03	0,03		0,04	0,0003	0,03		0,03		≥ 99,70
ML 1450	0,25	0,40	0,05	0,05	0,05		0,07	0,0003	0,10 - 0,20		0,03		≥ 99,50
ML 2319	0,20	0,30	5,80 - 6,80	0,20 - 0,40	0,02		0,10	0,0003	0,10 - 0,20	0,10 - 0,25	0,05	0,15	Rest / Solde
ML 4008	6,50 - 7,50	0,09	0,05	0,05	0,30 - 0,45		0,05	0,0003	0,04 - 0,15		0,05	0,15	Rest / Solde
ML 4043	4,50 - 6,00	0,60	0,30	0,15	0,20		0,10	0,0003	0,15		0,05	0,15	Rest / Solde
ML 4047	11,00 - 13,00	0,60	0,30	0,15	0,10		0,20	0,0003	0,15		0,05	0,15	Rest / Solde
ML4145	9,3 - 10,7	0,80	3,3 - 4,7	0,15	0,15		0,20	0,0003			0,05	0,15	Rest / Solde
ML 5087	0,25	0,40	0,05	0,70 - 1,10	4,50 - 5,20	0,05 - 0,25	0,25	0,0003	0,15	0,10 - 0,20	0,05	0,15	Rest / Solde
ML 5183	0,40	0,40	0,10	0,50 - 1,00	4,30 - 5,20	0,05 - 0,25	0,25	0,0003	0,15		0,05	0,15	Rest / Solde
ML 5356	0,25	0,40	0,10	0,05 - 0,20	4,50 - 5,50	0,05 - 0,20	0,10	0,0003	0,06 - 0,20		0,05	0,15	Rest / Solde
ML 5554	0,25	0,40	0,10	0,50 - 1,00	2,40 - 3,00	0,05 - 0,20	0,25	0,0003	0,05 - 0,20		0,05	0,15	Rest / Solde
ML 5556	0,25	0,40	0,10	0,60 - 1,00	5,00 - 5,50	0,05 - 0,20	0,20	0,0003	0,05 - 0,20		0,05	0,15	Rest / Solde
ML 5754	0,40	0,40	0,10	0,50	2,60 - 3,60	0,30	0,20	0,0003	0,15		0,05	0,15	Rest / Solde
ML AlMg6Zr	0,40	0,20	0,05	0,80 - 0,90	5,50 - 6,10		0,20	0,0003	0,02 - 0,15	0,08 - 0,12	0,05	0,15	Rest / Solde



Approvals / Certifications


	DNV-GL	ABS	DB	VdTUV	KRS	Bureau Veritas	Lloyd's
ML 4043			●	●			
ML 4047			●				
ML 5087	●		●	●		●	
ML5183	●	●	●	●	●	●	●
ML 5356	●	●	●	●	●	●	
ML 5556				●			

Spools and packaging / Types de bobines et emballages

TIG welding rods/ Baguette à souder



S100 0,5KG



S200 2KG




S300 6KG



B300 7KG



BS300 7KG



B400 18KG



B400 40KG



Jumbo-Drum 140 kg - 600X600X900 mm
Fût Jumbo 140 kg - 600X600X900 mm



Eco-Drum 40/80/100/120/200/250 kg
Fût 40/80/100/120/200/250 kg

Diameter Drum/ Diamètre Fûts [mm]	Weight kg / Poids Kg	
520	40	80
650	100	200
750	120	250